

PRODUCT DATA

Rust Veto A-2

An oil based rust preventative, providing indoor rust protection leaving a firm, waxy translucent film.

RUST VETO A-2 gives excellent protection to packaged items, dies and moulds, precision instruments and other highly finished parts stored indoors. This is the same rust preventive used in famous "**RUST VETO SPRAY**" aerosol applicator cans.

TYPICAL PHYSICAL PROPERTIES

Viscosity	2 cSt @ 40°C
Flash Point	46°C (T.O.C.)
Film Thickness	0.007 -0 .012 mm
Solids Content	20%

APPLICATIONS

RUST VETO A-2 is applied to highly finished parts before packaging. It protects tools, dies and gauges during storage and shipment.

FEATURES

- Easily applied
- Excellent rust protection
- Over 30 days in humidity cabinet test at 38°C; over one year indoor storage
- Easily removed by solvent or alkaline cleaners
- Film is translucent, firm, dry



HOUGHTON
Fluid Technology & Service Worldwide

HOUGHTON CANADA INC.

P.O. Box 113, Station "D"
100 Symes Rd.
Toronto, Ontario M6P 3J5
Ph (416) 763-4691 • Fx (416) 763-3167

HOW TO USE

Apply by dip, brush or spray at temperatures below 40°C. This deposits a film thickness from 0.007 -0 .012 mm with an approximate drying time of 20-25 minutes. Use xylol if a solvent thinner is needed.

CAUTION

Apply in a well ventilated area because of solvent fumes. During lengthy storage at temperatures under 18°C, this product tends to separate, but after warming, solids will again go into suspension.

REMOVAL

The film can easily be removed with solvent or alkaline cleaners

SHELF LIFE

Approximately one (1) year with adequate mixing before use

SHIPPING INFORMATION

RUST VETO A-2 is shipped in 20 litre pails, 205 liter drums and 1100 litre bulk.

SHIPPING CLASSIFICATION

Petroleum Oil or Grease - NOS

STORAGE/HANDLING/DISPOSABILITY

No health or safety hazards exist when **RUST VETO A-2** is stored, used and disposed of in accordance with instructions given on the Material Safety Data Sheet for this product.

WARRANTY

The information given here is considered to be correct and is offered for your consideration, investigation and verification. No warranties are expressed or implied, since the use of our products is beyond our control. Statements concerning the use of Houghton products are not to be construed as recommending the infringement of any patent.

February 9, 2005